FRONTIER WATERPROOF CERTIFICATE





Our Ref: SW/LS/GL/BR 10 December 2018

Report 331335/6 Page 1 of 2

Camira Fabrics Limited Meltham Mills Meltham Huddersfield West Yorkshire HD9 4AY

Contact: Katy Longstaff

DATE RECEIVED
QUALITY/REFERENCE
REPUTED FIBRE CONTENT
FABRIC DESCRIPTION
COLOUR/DESIGN
STYLE NUMBER
OF DEEP NUMBER

: VITA (C) : NOT GIVEN : LEATHER : AMERICANO : CALL 8348 : 934

23 OCT 2018

ORDER NUMBER : 934

PERFORMANCE STANDARD : NOT SPECIFIED



REQUEST: Hydrostatic head

- Wlena

L Sheridan

S. WISEMAN LABORATORY DIRECTOR

L. SHERIDAN LABORATORY MANAGER

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.





10 December 2018

Report 331335/6 PHYSICAL Page 2 of 2

Hydrostatic Head BS 3424-26:1990 Method 29A

 $\begin{array}{lll} \text{Sample area} & 100\text{cm}^2 \\ \text{Test atmosphere} & 20^{\circ}\text{C }65\% \text{ R.H} \\ \text{Water temperature} & 20^{\circ}\text{C} \\ \text{Rate of rise of water pressure} & 60\text{cm}/1\text{min} \end{array}$

As Received Test 1 >400 cms/H2O

Test 2 >400 cms/H2O Test 3 >400 cms/H2O Test 4 >400 cms/H2O Test 5 >400 cms/H2O

Mean >400 cms/H2O

